



ETHAPHOS 326

Antioxidant

Description

ETHAPHOS 326 Antioxidant is a high performance organophosphite that provides excellent color stability, reduces polymer degradation, and improves gas fading performance in many resins. ETHAPHOS 326 may be used in polyethylene, polypropylene, polystyrene, polyesters, elastomers, PVC and thermoplastics.

ETHAPHOS 326 is available in powder and granular form.

Typical Properties

Chemical Name: Bis (2,4-ditertbutylphenol) pentaerythritol diphosphite.
CAS #: 26741-53-7
Molecular Weight: 604
Form.....White powder or granule
Acid No (mgKOH/g).....1.0 max.
Capillary Melt Point ⁰C.....160 min
Phosphorous, %.....10.0 – 10.3
Bulk Density, 20 ⁰C, lbs/ft³.....27.0
Flash Point, PM Closed Cup, ⁰C.....168

Shipping Information

50 kg fiber drums
25 kg foil lined bags

Shipping Classification

Not regulated for transportation

Safety and Handling Information

Typical precautions should be taken and the product should be handled with care to prevent contamination of the environment. For specific information on the safe handling of this product, please refer to the material safety data sheet that is available upon request.

The information presented herein is believed to be accurate and reliable, but is presented without guarantee or responsibility on the part of Albemarle Corporation. It is the responsibility of the user to comply with all applicable laws and regulations and to provide for a safe workplace. The user should consider any health or safety hazards or information contained herein only as a guide, and should take those precautions which are necessary or prudent to instruct employees and to develop work practice procedures in order to promote a safe work environment. Further, nothing contained herein shall be taken as an inducement or recommendation to manufacture or use any of the herein materials or processes in violation of existing or future patents.

AMERICAS 451 Florida Street • Baton Rouge, Louisiana 70801-1765 • Tel: 225-388-7402 or 800-535-3030 • Fax: 225-388-7848 EUROPE Parc Scientifique Einstein • Rue du Bosquet 9 • B-1348 Louvain-la-Neuve Sud, Belgium • Tel: 32-10-48-1711 • Fax: 32-10-48-1717 EUROPE B116 • 95 Rue Du General De Gaulle • F-68802 Thann-Cedex, France • Tel: 33-3-8938-4600 • Fax: 33-3-8938-4601 ASIA PACIFIC 111 Somerset Road #13-03 • Singapore 238164 • Tel: 65-6732-6286 • Fax: 65-6737-4155 ASIA PACIFIC 16th Floor, Fukoku Seimei Building • 2-2, Uchisaiwaicho, 2-Chome • Chiyoda-ku, Tokyo 100, Japan • Tel: 81-3-5251-0791 • Fax: 81-3-3500-5623 ASIA PACIFIC China World Tower, Room 1317 • No. 1 Jian Guo Men Wai Avenue • Beijing 100004 China • Tel: 86-10-6505-4153 or 86-10-6505-4154 • Fax: 86-10-6505-4150

© 2005 Albemarle Corporation and ALBEMARLE are trademarks of Albemarle Corporation.

www.albemarle.com