TECHNICAL DATA SHEET

Date of Issue: 2018/02/20

iso-Propylmagnesium Chloride / Lithium Chloride, typ. 14 % solution in THF (typ. 1.3 M)

CAS-No. 745038-86-2

Molecular Formula C₃H₇ClMg / LiCl

Product Number 408450

APPLICATION Reagent for halogen/magnesium exchange reactions.

FURTHER INGREDIENTS

Tetrahydrofuran

CAS-No. 109-99-9 EC-No. 203-726-8

Isopropylmagnesium chloride

CAS-No. 1068-55-9 EC-No. 213-947-1

Lithium chloride

CAS-No. 7447-41-8 EC-No. 231-212-3

SPECIFICATION

iso-Propyl-MgCl 13.0 – 15.0 %

ratio LiCl / iso-Propyl-MgCl 0.9 - 1.1

METHOD OF ANALYSIS

Acidimetric titration of the hydrolized product for the determination of assay as total base. Detailed description available on request.

PHYSICAL PROPERTIES

Appearance liquid

Color yellowish to dark brown

The information presented herein is believed to be accurate and reliable, but is presented without guarantee or responsibility on the part of Albemarle Corporation and its subsidiaries and affiliates. It is the responsibility of the user to comply with all applicable laws and regulations and to provide for a safe workplace. The user should consider any health or safety hazards or information contained herein only as a guide, and should take those precautions which are necessary or prudent to instruct employees and to develop work practice procedures in order to promote a safe work environment. Further, nothing contained herein shall be taken as an inducement or recommendation to manufacture or use any of the herein materials or processes in violation of existing or future patent.



THF (typ. 1.3 M)

Product Number: 408450 Date of Issue: 2018/02/20

Crystallization temperature

< -10 °C

Flash point

-21.2 °C (Tetrahydrofuran)

Boiling point/boiling

range

66 °C (Tetrahydrofuran)

Density

ca. 0.98 g/cm3 at 20 °C

Water solubility

(Not applicable)

Molecular weight

145.24 g/mol

Thermal Stability

crystallisation below <-10°C

HANDLING & STORAGE

Handling iso-Propylmagnesium Chloride / Lithium Chloride should only be handled under

inert gas atmosphere. Avoid contact with eyes, skin and clothes as well as inhalation. Never add water, acids or oxidizing materials. In case of fire use dry extinguishers based on sodium chloride or limestone powder, never use water or

CO2. Pay attention to the Safety Data Sheet.

Storage iso-Propylmagnesium Chloride / Lithium Chloride should be stored in tightly closed

containers under exclusion of air and humidity. As material tends to crystallize at lower temperatures, it should be stored above >-10 °C. Under these conditions, stable over practically unlimited periods. Recommended retest date: six months

after date of delivery.

TRANSPORT & PACKAGING

UN number 3399

ADR	Class: 4.3	PG: I	Label: 4.3 (3)
RID	Class: 4.3	PG: I	Label: 4.3 (3)
IMDG	Class: 4.3	PG: I	Label: 4.3 (3)
IATA_C	Class: 4.3	PG: I	Packing instruction (cargo aircraft): 494
IATA_P	Class: 4.3	PG: I	

The information presented herein is believed to be accurate and reliable, but is presented without guarantee or responsibility on the part of Albemarle Corporation and its subsidiaries and affiliates. It is the responsibility of the user to comply with all applicable laws and regulations and to provide for a safe workplace. The user should consider any health or safety hazards or information contained herein only as a guide, and should take those precautions which are necessary or prudent to instruct employees and to develop work practice procedures in order to promote a safe work environment. Further, nothing contained herein shall be taken as an inducement or recommendation to manufacture or use any of the herein materials or processes in violation of existing or future patent.



THF (typ. 1.3 M)

Product Number: 408450 Date of Issue: 2018/02/20

Hazard pictograms









Signal Word Danger

H&P Phrases See Safety Data Sheet

The labelling is according to EU-GHS classification ((EG) 1272/2008) and may vary Labelling

in other countries. Please refer to the respective Safety Data Sheet for your country.

Packaging

Glass bottles of 100, 250, 500 and 1,000 ml. Steel bottles with volumes of 7.4, 27, 127 or 450 l. For safety reasons these are filled to a maximum of 90 %. Steel drums up to 200 l.

OTHER INFORMATION

Further Related

Our brochure(s)

Documents

Safety Data Sheet

Reactions

Turbo Grignards - Li powered metalation, Trifolder - Halogen/Metal Exchange



