

TECHNICAL DATA SHEET

Date of Issue: 2016/09/02

Zirconium Metal powder, Grade AB, suspended in acetone

CAS-No. 7440-67-7

EC-No. 231-176-9

Molecular Formula Zr

Product Number 453087

APPLICATION

Zirconium powders find application in various pyrotechnic areas. They are a source of heat for squibs and ignition devices for a variety of uses including automotive airbag inflators. For the production of highly reactive and quick fuze compositions in pyrotechnics for use in ammunition, explosives, airbags and safety belt pretensioners. They are also used in manufacture of flash cubes, electronic tubes, as well as as alloying agent with other metals.

FURTHER INGREDIENTS

Acetone

CAS-No. 67-64-1

EC-No. 200-662-2

Hafnium

CAS-No. 7440-58-6

EC-No. 231-166-4

SPECIFICATION

Zr total + Hf total min. 95 %

Hf approx. 2 % (natural content)

Ignition gain min. 28.4 %

Burning rate 12.5 +/- 7.5 s/50 cm

Surface area (BET) 1.3 +/- 0.5 m2/g

Auto ignition temperature 235 +/- 65 °C

Ca max. 0.1 %

Fe max. 0.1 %

Al max. 0.1 %

The information presented herein is believed to be accurate and reliable, but is presented without guarantee or responsibility on the part of Albemarle Corporation and its subsidiaries and affiliates. It is the responsibility of the user to comply with all applicable laws and regulations and to provide for a safe workplace. The user should consider any health or safety hazards or information contained herein only as a guide, and should take those precautions which are necessary or prudent to instruct employees and to develop work practice procedures in order to promote a safe work environment. Further, nothing contained herein shall be taken as an inducement or recommendation to manufacture or use any of the herein materials or processes in violation of existing or future patent.

Technical data sheets may change frequently. You can download the latest version from our website www.albemarle-lithium.com. Please contact us at www.albemarle-lithium.com/contact with questions.



Mg	max. 0.5 %
H	max. 0.2 %
Average particle size (Blaine)	1.9 +/- 0.4 µm
Particle size (by sieving)	min. 99.9 % < 45 µm

Particle size distribution (laser granulometer)

particle size	% less than
12 µm	100
7 µm	94 - 100
3 µm	75 - 94
0.75 µm	0 - 15

METHOD OF ANALYSIS

Determination of ignition gain, particle size distribution, average particle size, specific surface area (BET), combustion properties, gravimetric analysis of zirconium, spectrometric determination of impurities. For specific information on our standard methods of testing see the special metals sales program.

PHYSICAL PROPERTIES

Appearance	suspension
Color	dark gray
Melting point/ range	1,852 °C (Zirconium powder)
Flash point	-18 °C ([CAS: 67-64-1])
Boiling point/boiling range	55.8 - 56.6 °C ([CAS: 67-64-1])
Density	6.5 g/cm ³ at 20 °C (Zirconium powder) 0.79 g/cm ³ at 20 °C ([CAS: 67-64-1])
Bulk density	1,200 - 2,300 kg/m ³ (Zirconium powder)
Water solubility	(completely miscible) ([CAS: 67-64-1]) (practically insoluble) (Zirconium powder)
Additional Physical Properties	Delivery Form: packed under acetone

The information presented herein is believed to be accurate and reliable, but is presented without guarantee or responsibility on the part of Albemarle Corporation and its subsidiaries and affiliates. It is the responsibility of the user to comply with all applicable laws and regulations and to provide for a safe workplace. The user should consider any health or safety hazards or information contained herein only as a guide, and should take those precautions which are necessary or prudent to instruct employees and to develop work practice procedures in order to promote a safe work environment. Further, nothing contained herein shall be taken as an inducement or recommendation to manufacture or use any of the herein materials or processes in violation of existing or future patent.

Technical data sheets may change frequently. You can download the latest version from our website www.albemarle-lithium.com. Please contact us at www.albemarle-lithium.com/contact with questions.

HANDLING & STORAGE

Handling Highly flammable solid. Dust explosion hazard.

An ultra-fine, high-grade zirconium powder which ignites very easily and burns extremely rapidly at white heat. Zirconium metal powder is fairly inert to most chemical reagents, but at elevated temperatures is attacked by oxidizing agents and acids. Zirconium powder is attacked by cold acid fluoride solutions.

Keep away from flames, sparks and heat sources. Use ground connected metallic apparatus to avoid sudden ignition by electrostatic discharge. Self ignition is possible. Vacuum drying of suspensions is not recommended. Wear gloves, a face shield or safety goggles. In case of fire cover with dry sand or dry chemical/dolomite (powdered limestone). Never extinguish with water, carbon dioxide, or halocarbon.

See our safety data sheet and special precautionary advice for more information on safety.


Storage Store in tightly closed containers.

TRANSPORT & PACKAGING

UN number 1308

ADR	Class: 3	PG: II	Label: 3
RID	Class: 3	PG: II	Label: 3
IMDG	Class: 3	PG: II	Label: 3
IATA_C	Class: 3	PG: II	Packing instruction (cargo aircraft): 364
IATA_P	Class: 3	PG: II	Packing instruction (passenger aircraft): 353

Hazard pictograms



Signal Word Danger

H&P Phrases See Safety Data Sheet

Labelling The labelling is according to EU-GHS classification ((EG) 1272/2008) and may vary

The information presented herein is believed to be accurate and reliable, but is presented without guarantee or responsibility on the part of Albemarle Corporation and its subsidiaries and affiliates. It is the responsibility of the user to comply with all applicable laws and regulations and to provide for a safe workplace. The user should consider any health or safety hazards or information contained herein only as a guide, and should take those precautions which are necessary or prudent to instruct employees and to develop work practice procedures in order to promote a safe work environment. Further, nothing contained herein shall be taken as an inducement or recommendation to manufacture or use any of the herein materials or processes in violation of existing or future patent.

Technical data sheets may change frequently. You can download the latest version from our website www.albemarle-lithium.com. Please contact us at www.albemarle-lithium.com/contact with questions.

in other countries. Please refer to the respective Safety Data Sheet for your country.

Packaging

As suspension in PE-bottles overpacked in tin cans. Zirconium content 0.1 kg - 2.5 kg, acetone content min. 30 % by weight.

OTHER INFORMATION

Further Related Documents Safety Data Sheet

The information presented herein is believed to be accurate and reliable, but is presented without guarantee or responsibility on the part of Albemarle Corporation and its subsidiaries and affiliates. It is the responsibility of the user to comply with all applicable laws and regulations and to provide for a safe workplace. The user should consider any health or safety hazards or information contained herein only as a guide, and should take those precautions which are necessary or prudent to instruct employees and to develop work practice procedures in order to promote a safe work environment. Further, nothing contained herein shall be taken as an inducement or recommendation to manufacture or use any of the herein materials or processes in violation of existing or future patent.

Technical data sheets may change frequently. You can download the latest version from our website www.albemarle-lithium.com. Please contact us at www.albemarle-lithium.com/contact with questions.

