


SAYTEX® HP-7010 Flame Retardant

DESCRIPTION

Brominated polystyrene
SAYTEX HP-7010 flame retardant is a polymeric additive containing thermally stable, aromatic bromine. It is available in powder (HP-7010P) or granule form (HP-7010G).



where x and y are approximately 2000 and 2.7, respectively


APPLICATIONS

SAYTEX HP-7010 flame retardant provides outstanding thermal stability and electrical performance. It is particularly suitable for engineering plastic applications such as polyesters (PET, PBT, PCT) and polyamides (nylons).

BENEFITS AND FEATURES

SAYTEX HP-7010 flame retardant has outstanding thermal stability. It is an ideal choice for high temperature applications such as engineering plastics. Due to its stability, it can often be used where other flame retardants fail to survive. Due to its polymeric structure, SAYTEX HP-7010 flame retardant is non-blooming in all applications. Excellent electrical properties provide yet another reason to choose this flame retardant for demanding engineering plastic applications.

TYPICAL PROPERTIES



% Bromine (theoretical)	68.5
Tg (°C)	182
Appearance/form	White powder or granules
Specific Gravity	2.15
Refractive index	1.68
Solubility in: (wt. % at 25°C)	
Water	<0.01
Acetone	<0.01
Methanol	<0.01
Toluene	0.7
Styrene monomer	11.2
TGA (TA Instruments model Q500 V6.7 10°C/ min under N ₂)	
1% weight loss, °C	343
5% weight loss, °C	370
10% weight loss, °C	380
50% weight loss, °C	406
90% weight loss, °C	430

These properties are typical but do not constitute a specification either in part or as a whole. Specification data is available on request from sales, customer service or customer technical service.

CHEMICAL REGISTRATION NUMBER

CAS: 88497-56-7
EINECS: exempt
MITI: 6-1579

RESPONSIBLE CARE

Albemarle is committed to the safety and well-being of our customers, employees and the community at large. Material safety data sheets (MSDS) are available upon request.



NORTH AMERICA 4250 Congress Street, Suite 900 • Charlotte, NC 28209 • Tel: +1 980 299 5700
EUROPE Parc Scientifique Einstein, Rue du Bosquet 9, 1348 • Louvain-la-Neuve, Belgium • Tel: +32 10 48 17 11
LATIN AMERICA Av. Brigadeiro Faria Lima, 1461 – sala 131-B • Sao Paulo, SP Brazil, 01451-001 • Tel: +55 11 99655-2288
CHINA Room 3202, No. 757 Mengzi Road, Gopher Center, Huangpu District • Shanghai, PRC. 200023 • Tel: 86.21.6103.8666

The information presented herein is believed to be accurate and reliable, but is presented without guarantee or responsibility on the part of Albemarle Corporation and its subsidiaries to ensure the accuracy or reliability of the information. It is the responsibility of the user to comply with all applicable laws and regulations and to provide for a safe workplace. The user should consider all information contained herein only as a guide, and should take precautions that the user considers necessary or prudent to promote a safe work environment, such as considering all applicable health and safety hazards, developing safe work practice procedures and properly instructing employees. Further, nothing contained herein shall be taken as an inducement or recommendation to manufacture or use any of the materials or processes mentioned herein in violation of existing or pending patents.