

## TECHNICAL DATA SHEET

Date of Issue: 2026/05/28

# Zirconium Metal powder, Grade GH, aqueous suspension

CAS-No.	7440-67-7
EC-No.	231-176-9
REACH No.	01-2119490102-49-0004
Molecular formula	Zr
Product number	10001966

### APPLICATION

For the manufacture of highly effective getters, usually activated by dehydration; as a zirconium component in powder metallurgy; for flares and tracers in pyrotechnics.

### SPECIFICATION

Zr + Hf total	min. 98.0 %
Hf	approx. 2 % (natural content)
H	0.55 - 1 %
Ti	max. 0.3 %
Si	max. 0.3 %
Mg	max. 0.2 %
Ca total	max. 0.2 %
Fe	max. 0.08 %
Al	max. 0.3 %
Cl	max. 0.05 %

The information presented herein is believed to be accurate and reliable, but is presented without guarantee or responsibility on the part of Albemarle Corporation and its subsidiaries and affiliates. It is the responsibility of the user to comply with all applicable laws and regulations and to provide for a safe workplace. The user should consider any health or safety hazards or information contained herein only as a guide, and should take those precautions which are necessary or prudent to instruct employees and to develop work practice procedures in order to promote a safe work environment. Further, nothing contained herein shall be taken as an inducement or recommendation to manufacture or use any of the herein materials or processes in violation of existing or future patent.

Technical data sheets may change frequently. You can download the latest version from our website [www.albemarle.com](http://www.albemarle.com).

Please contact us at [www.albemarle.com/contact](http://www.albemarle.com/contact) with questions.



Product number: 10001966  
Date of Issue: 2026/05/28

---

Ca soluble	max. 0.03 %
------------	-------------

---

## METHOD OF ANALYSIS

Determination of oxidation value, particle size distribution, average particle size; specific surface area and combustion properties; gravimetric analysis of zirconium, verification of nitrogen content and accompanying impurities by special analytical methods.

---

## PHYSICAL PROPERTIES

Appearance	suspension
Color	black to gray
Melting point/ range	1,855 °C (Zirconium)
Boiling point/boiling range	3,577 °C (Zirconium)
Density	6.43 g/cm <sup>3</sup> at 20 °C Method: OECD Test Guideline 109 (Zirconium)
Water solubility	(practically insoluble)
Grain Size	min. 99.9 % < 45 µm by sieving APS 5.5 +/- 1 µm acc. to Blaine
Additional Physical Properties	Ignition Point: 215 - 310 °C      Combustion Rate (Albemarle standard): 460 +/- 75 sec/50 cm      Gain on Ignition: min. 32.3 % (weight increase by combustion)      Apparent density: approx. 1.9-2.4 g/ccm

---

The information presented herein is believed to be accurate and reliable, but is presented without guarantee or responsibility on the part of Albemarle Corporation and its subsidiaries and affiliates. It is the responsibility of the user to comply with all applicable laws and regulations and to provide for a safe workplace. The user should consider any health or safety hazards or information contained herein only as a guide, and should take those precautions which are necessary or prudent to instruct employees and to develop work practice procedures in order to promote a safe work environment. Further, nothing contained herein shall be taken as an inducement or recommendation to manufacture or use any of the herein materials or processes in violation of existing or future patent.

## HANDLING & STORAGE

**Handling** Highly flammable solid. Dust explosion hazard. A mixture of zirconium metal and zirconium hydride powder of high purity and low oxide content. Due to its higher content in hydrogen less ignitable than other grades. Keep away from flames, sparks and heat sources; use ground-connected metallic apparatus to avoid sudden ignition by electrostatic discharge; self-ignition is possible; vacuum-drying of suspensions not recommended; wear gloves, a face shield or goggles; in case of fire, cover only with sand, limestone or with a dry extinguishing powder suitable for metal fires class D; **DO NOT USE WATER!** Refer to our safety data sheet and special precautionary advice for specific safety information!

---

## TRANSPORT & PACKAGING

UN number 1358

ADR	Class: 4.1	PG: II	Label: 4.1
RID	Class: 4.1	PG: II	Label: 4.1
IMDG	Class: 4.1	PG: II	Label: 4.1
IATA_C	Class: 4.1	PG: II	Packing instruction (cargo aircraft): 448
IATA_P	Class: 4.1	PG: II	Packing instruction (passenger aircraft): 445

Hazard pictograms

**Signal Word** Danger**H&P Phrases** See Safety Data Sheet**Labelling** The labelling is according to EU-GHS classification ((EG) 1272/2008) and may vary in other countries. Please refer to the respective Safety Data Sheet for your country.

---

The information presented herein is believed to be accurate and reliable, but is presented without guarantee or responsibility on the part of Albemarle Corporation and its subsidiaries and affiliates. It is the responsibility of the user to comply with all applicable laws and regulations and to provide for a safe workplace. The user should consider any health or safety hazards or information contained herein only as a guide, and should take those precautions which are necessary or prudent to instruct employees and to develop work practice procedures in order to promote a safe work environment. Further, nothing contained herein shall be taken as an inducement or recommendation to manufacture or use any of the herein materials or processes in violation of existing or future patent.

Product number: 10001966

Date of Issue: 2026/05/28

---

## Packaging

In PE-bottles with max. 2.5 kg capacity, water content min. 30 %.

---

## OTHER INFORMATION

Further Related Documents      Safety Data Sheet

---

The information presented herein is believed to be accurate and reliable, but is presented without guarantee or responsibility on the part of Albemarle Corporation and its subsidiaries and affiliates. It is the responsibility of the user to comply with all applicable laws and regulations and to provide for a safe workplace. The user should consider any health or safety hazards or information contained herein only as a guide, and should take those precautions which are necessary or prudent to instruct employees and to develop work practice procedures in order to promote a safe work environment. Further, nothing contained herein shall be taken as an inducement or recommendation to manufacture or use any of the herein materials or processes in violation of existing or future patent.

Technical data sheets may change frequently. You can download the latest version from our website [www.albemarle.com](http://www.albemarle.com).

Please contact us at [www.albemarle.com/contact](http://www.albemarle.com/contact) with questions.

