

TECHNICAL DATA SHEET

Date of Issue: 2021/07/22

Cesium Fluoride, purity min. 99.9 %, superdry

CAS-No.	13400-13-0
EC-No.	236-487-3
REACH No.	01-2120774388-39-0000
Molecular formula	Cs-F
Product number	10001883

APPLICATION

Cesium fluoride is a fluorination agent for halide exchange reactions. It is a versatile base in organic synthesis and can be used in e.g. in polymerization reactions or in brazing fluxes.

PURITY

min. 99.9 %

SPECIFICATION

Li	max. 5 ppm
Na	max. 100 ppm
K	max. 300 ppm
Rb	max. 100 ppm
Ca	max. 5 ppm
Mg	max. 5 ppm
Sr	max. 5 ppm
Ba	max. 5 ppm

The information presented herein is believed to be accurate and reliable, but is presented without guarantee or responsibility on the part of Albemarle Corporation and its subsidiaries and affiliates. It is the responsibility of the user to comply with all applicable laws and regulations and to provide for a safe workplace. The user should consider any health or safety hazards or information contained herein only as a guide, and should take those precautions which are necessary or prudent to instruct employees and to develop work practice procedures in order to promote a safe work environment. Further, nothing contained herein shall be taken as an inducement or recommendation to manufacture or use any of the herein materials or processes in violation of existing or future patent.

Technical data sheets may change frequently. You can download the latest version from our website

www.albemarle-lithium.com. Please contact us at www.albemarle-lithium.com/contact with questions.



Product number: 10001883

Date of Issue: 2021/07/22

Al	max. 5 ppm
Fe	max. 10 ppm
Cr	max. 3 ppm
P2O5	max. 5 ppm
SO4	max. 100 ppm
CO3	max. 100 ppm
Cl	max. 100 ppm
H2O (Karl Fischer)	max. 0.03 %
free acid as HF	max. 0.1 %

Deliveries are accompanied by a lot specific certificate of analysis. If any of these values is critical to your application, please let us know.

PHYSICAL PROPERTIES

Appearance	Crystalline powder
Colour	white
Melting point/range	703 °C at 1,013 hPa Method: OECD Test Guideline 102
Flash point	(Not applicable)
Boiling point/boiling range	1,251 °C
Density	4.59 g/cm ³ at 20 °C Method: OECD Test Guideline 109
Bulk density	2,000 - 3,200 kg/m ³
Water solubility	> 1,000 g/l at 20 °C Method: OECD Test Guideline 105
Molecular weight	151.90 g/mol

The information presented herein is believed to be accurate and reliable, but is presented without guarantee or responsibility on the part of Albemarle Corporation and its subsidiaries and affiliates. It is the responsibility of the user to comply with all applicable laws and regulations and to provide for a safe workplace. The user should consider any health or safety hazards or information contained herein only as a guide, and should take those precautions which are necessary or prudent to instruct employees and to develop work practice procedures in order to promote a safe work environment. Further, nothing contained herein shall be taken as an inducement or recommendation to manufacture or use any of the herein materials or processes in violation of existing or future patent.

Technical data sheets may change frequently. You can download the latest version from our website

www.albemarle-lithium.com. Please contact us at www.albemarle-lithium.com/contact with questions.

HANDLING & STORAGE

Handling	Handling in moist air should be avoided. Safe handling requires the safety precautions typical for inorganic fluorides. Thus, eyes or skin should not be exposed to cesium fluoride, otherwise severe irritation may result. Ingestion must be avoided because of the toxicity of fluoride.
Storage	Because of its hygroscopicity cesium fluoride should be stored in tightly closed containers.

TRANSPORT & PACKAGING

ADR
Not regulated as a dangerous good

Hazard pictograms



Signal word	Danger
H&P Phrases	See Safety Data Sheet
Labelling	The labelling is according to EU-GHS classification ((EG) 1272/2008) and may vary in other countries. Please refer to the respective Safety Data Sheet for your country.

Packaging

Glass bottles or PE bags with aluminium barrier in drums (fiber drums, clamping ring drums, steel drums, steel drums with polypropylene inner lining). The aluminium barrier prevents diffusion of moisture into the product. Alternative packaging on request. Smaller units are available at surcharge.

The information presented herein is believed to be accurate and reliable, but is presented without guarantee or responsibility on the part of Albemarle Corporation and its subsidiaries and affiliates. It is the responsibility of the user to comply with all applicable laws and regulations and to provide for a safe workplace. The user should consider any health or safety hazards or information contained herein only as a guide, and should take those precautions which are necessary or prudent to instruct employees and to develop work practice procedures in order to promote a safe work environment. Further, nothing contained herein shall be taken as an inducement or recommendation to manufacture or use any of the herein materials or processes in violation of existing or future patent.

OTHER INFORMATION

Further Related Documents Safety Data Sheet

The information presented herein is believed to be accurate and reliable, but is presented without guarantee or responsibility on the part of Albemarle Corporation and its subsidiaries and affiliates. It is the responsibility of the user to comply with all applicable laws and regulations and to provide for a safe workplace. The user should consider any health or safety hazards or information contained herein only as a guide, and should take those precautions which are necessary or prudent to instruct employees and to develop work practice procedures in order to promote a safe work environment. Further, nothing contained herein shall be taken as an inducement or recommendation to manufacture or use any of the herein materials or processes in violation of existing or future patent.