

TECHNICAL DATA SHEET

Date of Issue: 2021/07/22

Zirconium Metal powder, Grade XP, dry

CAS-No.	7440-67-7
EC-No.	231-176-9
REACH No.	01-2119490102-49-0004
Molecular formula	Zr
Product number	10001970

APPLICATION

In vacuum technology as a getter material; in powder metallurgy as an alloying constituent; in pyrotechnics for the manufacture of high energy initiators, fuzes and thermal batteries.

SPECIFICATION

Zr(active) + Hf(active)	min. 95 %
Auto ignition temperature	approx. 250 °C
Average particle size (Blaine)	6 +/- 2 µm

METHOD OF ANALYSIS

Determination of oxidation value, particle distribution, average particle size, specific surface area and combustion characteristics; gravimetric analysis of zirconium, determination of hydrogen content and impurities. For specific information on Albemarle standard determination methods see our delivery program.

The information presented herein is believed to be accurate and reliable, but is presented without guarantee or responsibility on the part of Albemarle Corporation and its subsidiaries and affiliates. It is the responsibility of the user to comply with all applicable laws and regulations and to provide for a safe workplace. The user should consider any health or safety hazards or information contained herein only as a guide, and should take those precautions which are necessary or prudent to instruct employees and to develop work practice procedures in order to promote a safe work environment. Further, nothing contained herein shall be taken as an inducement or recommendation to manufacture or use any of the herein materials or processes in violation of existing or future patent.

Technical data sheets may change frequently. You can download the latest version from our website

www.albemarle-lithium.com. Please contact us at www.albemarle-lithium.com/contact with questions.



PHYSICAL PROPERTIES

Appearance	powder
Colour	dark grey
Melting point/range	1,855 °C (Information taken from reference works and the literature.)
Boiling point/boiling range	3,577 °C (Information taken from reference works and the literature.)
Density	6.434 g/cm ³ at 20 °C Method: OECD Test Guideline 109
Bulk density	1,200 - 2,300 kg/m ³
Water solubility	< 0.00005 g/l at 20 °C Method: OECD Test Guideline 29

HANDLING & STORAGE

Handling	Highly flammable solid. Dust explosion hazard. A zirconium powder with maximum metal content, which burns at white heat. Compared with its relative coarse particle size it burns very fast. Keep away from flames, sparks and heat sources; use ground-connected metallic apparatus to avoid sudden ignition by electrostatic discharge; self-ignition is possible; vacuum-drying of suspensions not recommended; wear gloves, a face shield or goggles; in case of fire, cover only with dry sand, limestone or with a dry extinguishing powder suitable for metal fires class D; DO NOT USE WATER! Refer to our safety data sheet and special precautionary advice for specific safety information!
----------	---

The information presented herein is believed to be accurate and reliable, but is presented without guarantee or responsibility on the part of Albemarle Corporation and its subsidiaries and affiliates. It is the responsibility of the user to comply with all applicable laws and regulations and to provide for a safe workplace. The user should consider any health or safety hazards or information contained herein only as a guide, and should take those precautions which are necessary or prudent to instruct employees and to develop work practice procedures in order to promote a safe work environment. Further, nothing contained herein shall be taken as an inducement or recommendation to manufacture or use any of the herein materials or processes in violation of existing or future patent.

TRANSPORT & PACKAGING

UN number 2008

ADR	Class: 4.2	PG: I	Label: 4.2
RID	Class: 4.2	PG: I	Label: 4.2
IMDG	Class: 4.2	PG: I	Label: 4.2
IATA_C	Class: 4.2		
IATA_P	Class: 4.2		

Hazard pictograms



Signal word

Danger

H&P Phrases

See Safety Data Sheet

Labelling

The labelling is according to EU-GHS classification ((EG) 1272/2008) and may vary in other countries. Please refer to the respective Safety Data Sheet for your country.

Packaging

In tin cans with a content of max. 5 kg capacity.

OTHER INFORMATION

Further Related Documents

Safety Data Sheet

The information presented herein is believed to be accurate and reliable, but is presented without guarantee or responsibility on the part of Albemarle Corporation and its subsidiaries and affiliates. It is the responsibility of the user to comply with all applicable laws and regulations and to provide for a safe workplace. The user should consider any health or safety hazards or information contained herein only as a guide, and should take those precautions which are necessary or prudent to instruct employees and to develop work practice procedures in order to promote a safe work environment. Further, nothing contained herein shall be taken as an inducement or recommendation to manufacture or use any of the herein materials or processes in violation of existing or future patent.

Technical data sheets may change frequently. You can download the latest version from our website

www.albemarle-lithium.com. Please contact us at www.albemarle-lithium.com/contact with questions.