

TECHNICAL DATA SHEET

Date of Issue: 2017/01/26

Spodumene Concentrate, SC 6.8

CAS-No. 1302-37-0

Molecular Formula $AlLi(SiO_3)_2$

Product Number 402209

APPLICATION

Spodumene is used in glasses, glass-ceramics, porcelain enamels, whitewares, and glazes due to the powerful fluxing properties of lithia. It possesses a very low thermal expansion and reduces the viscosity of the glass mass. It contributes to brilliancy and strength of the glass. Spodumene is also used in metallurgical applications, i.a. in continuous casting powders, anti-veining agents and as additive in foundry feeder production.

FURTHER INGREDIENTS

Feldspar

CAS-No. 68476-25-5

EC-No. 270-666-7

Quartz (SiO₂)

CAS-No. 14808-60-7

EC-No. 238-878-4

SPECIFICATION

	Specification	Method of Analysis
Li ₂ O	min. 6.8 %	AAS
Al ₂ O ₃	min. 24.5 %	XRF
SiO ₂	min. 63.5 %	XRF
Fe ₂ O ₃	max. 0.20 %	XRF
Na ₂ O	max. 0.5 %	XRF
K ₂ O	max. 0.6 %	XRF
P ₂ O ₅	max. 0.5 %	XRF
LOI (1000 °C)	max. 0.7 %	gravimetric

The information presented herein is believed to be accurate and reliable, but is presented without guarantee or responsibility on the part of Albemarle Corporation and its subsidiaries and affiliates. It is the responsibility of the user to comply with all applicable laws and regulations and to provide for a safe workplace. The user should consider any health or safety hazards or information contained herein only as a guide, and should take those precautions which are necessary or prudent to instruct employees and to develop work practice procedures in order to promote a safe work environment. Further, nothing contained herein shall be taken as an inducement or recommendation to manufacture or use any of the herein materials or processes in violation of existing or future patent.

Technical data sheets may change frequently. You can download the latest version from our website www.albemarle-lithium.com. Please contact us at www.albemarle-lithium.com/contact with questions.

PHYSICAL PROPERTIES

Appearance	powder
Color	white to beige
Melting point/ range	from 1,375 °C
Density	3.1 g/cm ³
Bulk density	1,300 kg/m ³
Water solubility	(immiscible)

Grain Size	Grain Size	Guaranteed
	> 125 µm	max. 3.0 %
	< 75 µm	min. 80 %

Additional Physical Properties Spodumene is a mineral with the general formula [LiAl(Si₂O₆)]

Major Composition	Weight %
Spodumene	~ 89 %
Quartz	~ 8 %
Feldspar	~ 2 %

HANDLING & STORAGE

Handling Observe official safety regulations

Storage Store in dry conditions as material is produced and consumed as a dried product.
Do not store together with volatile chemicals as they may be absorbed into the product.

TRANSPORT & PACKAGING

ADR
Not regulated as a dangerous good

Packaging

big bags (1000 kg) on pallet

The information presented herein is believed to be accurate and reliable, but is presented without guarantee or responsibility on the part of Albemarle Corporation and its subsidiaries and affiliates. It is the responsibility of the user to comply with all applicable laws and regulations and to provide for a safe workplace. The user should consider any health or safety hazards or information contained herein only as a guide, and should take those precautions which are necessary or prudent to instruct employees and to develop work practice procedures in order to promote a safe work environment. Further, nothing contained herein shall be taken as an inducement or recommendation to manufacture or use any of the herein materials or processes in violation of existing or future patent.

Technical data sheets may change frequently. You can download the latest version from our website www.albemarle-lithium.com. Please contact us at www.albemarle-lithium.com/contact with questions.

OTHER INFORMATION

Further Related Documents Safety Data Sheet

The information presented herein is believed to be accurate and reliable, but is presented without guarantee or responsibility on the part of Albemarle Corporation and its subsidiaries and affiliates. It is the responsibility of the user to comply with all applicable laws and regulations and to provide for a safe workplace. The user should consider any health or safety hazards or information contained herein only as a guide, and should take those precautions which are necessary or prudent to instruct employees and to develop work practice procedures in order to promote a safe work environment. Further, nothing contained herein shall be taken as an inducement or recommendation to manufacture or use any of the herein materials or processes in violation of existing or future patent.

Technical data sheets may change frequently. You can download the latest version from our website www.albemarle-lithium.com. Please contact us at www.albemarle-lithium.com/contact with questions.

