

TECHNICAL DATA SHEET

Date of Issue: 2017/09/06

Vinylmagnesium Chloride, typ. 16.5 % solution in THF (typ. 1.9 M)

CAS-No.	3536-96-7
EC-No.	222-575-9
REACH No.	01-2120065573-54
Molecular Formula	C_2H_3ClMg
Product Number	408464

APPLICATION	Grignard-reactions: reagent for the introduction of the vinyl group.
-------------	--

FURTHER INGREDIENTS

Tetrahydrofuran

CAS-No.	109-99-9
EC-No.	203-726-8

SPECIFICATION

Vinylmagnesium Chloride: 15.5 – 17.5 %

METHOD OF ANALYSIS

Acidimetric titration of the hydrolized product for the determination of assay as total base. Detailed description available on request.

PHYSICAL PROPERTIES

Appearance	liquid
Color	yellowish to dark brown

The information presented herein is believed to be accurate and reliable, but is presented without guarantee or responsibility on the part of Albemarle Corporation and its subsidiaries and affiliates. It is the responsibility of the user to comply with all applicable laws and regulations and to provide for a safe workplace. The user should consider any health or safety hazards or information contained herein only as a guide, and should take those precautions which are necessary or prudent to instruct employees and to develop work practice procedures in order to promote a safe work environment. Further, nothing contained herein shall be taken as an inducement or recommendation to manufacture or use any of the herein materials or processes in violation of existing or future patent.

Technical data sheets may change frequently. You can download the latest version from our website www.albemarle-lithium.com. Please contact us at www.albemarle-lithium.com/contact with questions.



Crystallization temperature	<= 5 °C
Flash point	-21.2 °C (Tetrahydrofuran)
Boiling point/boiling range	66 °C (Tetrahydrofuran)
Density	0.98 g/cm3 at 20 °C
Water solubility	(Not applicable)
Molecular weight	86.80 g/mol
Thermal Stability	Crystallization below around 5 °C

HANDLING & STORAGE

Handling	Vinylmagnesium Chloride should only be handled under inert gas atmosphere. Avoid contact with eyes, skin and clothes as well as inhalation. Never add water, acids or oxidizing materials. In case of fire use dry extinguishers based on sodium chloride or limestone powder, never use water or CO2. Pay attention to the Safety Data Sheet.
Storage	Vinylmagnesium Chloride should be stored in tightly closed containers under exclusion of air and humidity. As material tends to crystallize at lower temperatures, it should be stored above 15 °C. Storage temperatures above 25 °C should be avoided due to slow irreversible oligomerization of the product. Recommended retest date: three months after date of delivery.

TRANSPORT & PACKAGING

UN number 3399

ADR	Class: 4.3	PG: I	Label: 4.3 (3)
RID	Class: 4.3	PG: I	Label: 4.3 (3)
IMDG	Class: 4.3	PG: I	Label: 4.3 (3)
IATA_C	Class: 4.3	PG: I	Packing instruction (cargo aircraft): 494
IATA_P	Class: 4.3	PG: I	

The information presented herein is believed to be accurate and reliable, but is presented without guarantee or responsibility on the part of Albemarle Corporation and its subsidiaries and affiliates. It is the responsibility of the user to comply with all applicable laws and regulations and to provide for a safe workplace. The user should consider any health or safety hazards or information contained herein only as a guide, and should take those precautions which are necessary or prudent to instruct employees and to develop work practice procedures in order to promote a safe work environment. Further, nothing contained herein shall be taken as an inducement or recommendation to manufacture or use any of the herein materials or processes in violation of existing or future patent.

Technical data sheets may change frequently. You can download the latest version from our website www.albemarle-lithium.com. Please contact us at www.albemarle-lithium.com/contact with questions.

Hazard pictograms



Signal Word Danger

H&P Phrases See Safety Data Sheet

Labelling The labelling is according to EU-GHS classification ((EG) 1272/2008) and may vary in other countries. Please refer to the respective Safety Data Sheet for your country.

Packaging

Glass bottles of 100, 250, 500 and 1,000 ml. Steel bottles with volumes of 7.4, 27, 127 or 450 l. For safety reasons these are filled to a maximum of 90 %. Steel drums up to 200 l.

OTHER INFORMATION

Further Related Documents Safety Data Sheet

Our brochure(s) Organomagnesium Compounds, Trifolder - CC-Coupling Reactions in Organic Synthesis

The information presented herein is believed to be accurate and reliable, but is presented without guarantee or responsibility on the part of Albemarle Corporation and its subsidiaries and affiliates. It is the responsibility of the user to comply with all applicable laws and regulations and to provide for a safe workplace. The user should consider any health or safety hazards or information contained herein only as a guide, and should take those precautions which are necessary or prudent to instruct employees and to develop work practice procedures in order to promote a safe work environment. Further, nothing contained herein shall be taken as an inducement or recommendation to manufacture or use any of the herein materials or processes in violation of existing or future patent.

Technical data sheets may change frequently. You can download the latest version from our website www.albemarle-lithium.com. Please contact us at www.albemarle-lithium.com/contact with questions.