

# TECHNICAL DATA SHEET

Date of Issue: 2017/09/06

## Phenylmagnesium Bromide, typ. 15 % solution in THF (typ. 0.8 M)

CAS-No.	100-58-3
EC-No.	202-867-2
Molecular Formula	C <sub>6</sub> H <sub>5</sub> MgBr
Product Number	408545

---

**APPLICATION** Grignard-reactions: reagent for the introduction of the phenyl group.

---

### FURTHER INGREDIENTS

Tetrahydrofuran

CAS-No.	109-99-9
EC-No.	203-726-8

Benzene

CAS-No.	71-43-2
EC-No.	200-753-7

### SPECIFICATION

Phenylmagnesium Bromide: 14.0 – 16.0 %

---

### METHOD OF ANALYSIS

Determination of assay as total base by acidimetric titration after hydrolysis; detailed description available on request.

---

### PHYSICAL PROPERTIES

Appearance	liquid
Color	brown

---

The information presented herein is believed to be accurate and reliable, but is presented without guarantee or responsibility on the part of Albemarle Corporation and its subsidiaries and affiliates. It is the responsibility of the user to comply with all applicable laws and regulations and to provide for a safe workplace. The user should consider any health or safety hazards or information contained herein only as a guide, and should take those precautions which are necessary or prudent to instruct employees and to develop work practice procedures in order to promote a safe work environment. Further, nothing contained herein shall be taken as an inducement or recommendation to manufacture or use any of the herein materials or processes in violation of existing or future patent.

Technical data sheets may change frequently. You can download the latest version from our website [www.albemarle-lithium.com](http://www.albemarle-lithium.com). Please contact us at [www.albemarle-lithium.com/contact](http://www.albemarle-lithium.com/contact) with questions.



Crystallization temperature	< 20 °C
Flash point	-21.2 °C (Tetrahydrofuran)
Boiling point/boiling range	66 °C (Tetrahydrofuran)
Density	ca. 0.98 g/cm <sup>3</sup> at 20 °C
Water solubility	(Not applicable)
Molecular weight	181.31 g/mol
Thermal Stability	crystallisation below around 20 °C

## HANDLING & STORAGE

Handling	Organomagnesium compounds should only be handled under inert gas (nitrogen or argon). Never add water, acids or oxidizing materials to the product. In case of fire use dry extinguishers on basis of sodium chloride or limestone powder. Never use water or CO <sub>2</sub> -extinguishers. Pay attention to official safety regulations (see also: "Transport regulations" and "GHS Hazard Pictograms").
Storage	Under exclusion of air and humidity stable over practically unlimited periods. As material tends to crystallize it should be stored above 20 °C. Precipitates can be redissolved by warming and appropriate homogenization. Keep container dry and tightly closed.

## TRANSPORT & PACKAGING

UN number 2924

ADR	Class: 3	PG: II	Label: 3 (8)
RID	Class: 3	PG: II	Label: 3 (8)
IMDG	Class: 3	PG: II	Label: 3 (8)
IATA_C	Class: 3	PG: II	Packing instruction (cargo aircraft): 363
IATA_P	Class: 3	PG: II	Packing instruction (passenger aircraft): 352

The information presented herein is believed to be accurate and reliable, but is presented without guarantee or responsibility on the part of Albemarle Corporation and its subsidiaries and affiliates. It is the responsibility of the user to comply with all applicable laws and regulations and to provide for a safe workplace. The user should consider any health or safety hazards or information contained herein only as a guide, and should take those precautions which are necessary or prudent to instruct employees and to develop work practice procedures in order to promote a safe work environment. Further, nothing contained herein shall be taken as an inducement or recommendation to manufacture or use any of the herein materials or processes in violation of existing or future patent.

Hazard pictograms



Signal Word                      Danger

H&P Phrases                      See Safety Data Sheet

Labelling                              The labelling is according to EU-GHS classification ((EG) 1272/2008) and may vary in other countries. Please refer to the respective Safety Data Sheet for your country.

Packaging

Glass bottles of 100, 250, 500 and 1,000 ml. Steel drums up to 200 l. Steel bottles with volumes of 7.4, 27, 127 and 450 l. For safety reasons these are filled to a maximum of 90 %.

---

OTHER INFORMATION

Further Related                      Safety Data Sheet  
Documents

Our brochure(s)                      Organomagnesium Compounds

---

The information presented herein is believed to be accurate and reliable, but is presented without guarantee or responsibility on the part of Albemarle Corporation and its subsidiaries and affiliates. It is the responsibility of the user to comply with all applicable laws and regulations and to provide for a safe workplace. The user should consider any health or safety hazards or information contained herein only as a guide, and should take those precautions which are necessary or prudent to instruct employees and to develop work practice procedures in order to promote a safe work environment. Further, nothing contained herein shall be taken as an inducement or recommendation to manufacture or use any of the herein materials or processes in violation of existing or future patent.

Technical data sheets may change frequently. You can download the latest version from our website [www.albemarle-lithium.com](http://www.albemarle-lithium.com). Please contact us at [www.albemarle-lithium.com/contact](http://www.albemarle-lithium.com/contact) with questions.