


TECHNICAL DATA SHEET

Date of Issue: 2017/09/06

iso-Propylmagnesium Bromide, typ.
40% solution in 2-Methyl-THF (typ. 3
M)



CAS-No.	920-39-8
EC-No.	213-056-8
Molecular Formula	$(\text{CH}_3)_2\text{CH-MgBr}$
Product Number	408586

APPLICATION Grignard reactions; reagent for introduction of the iso-propyl group.

FURTHER INGREDIENTS

2-Methyltetrahydrofuran

CAS-No.	96-47-9
EC-No.	202-507-4

SPECIFICATION

iso-Propylmagnesium Bromide: 38,0 - 41,0 %

METHOD OF ANALYSIS

Determination of assay as total base by acidimetric titration after hydrolysis; detailed description available on request.

PHYSICAL PROPERTIES

Appearance	liquid
Color	brown

The information presented herein is believed to be accurate and reliable, but is presented without guarantee or responsibility on the part of Albemarle Corporation and its subsidiaries and affiliates. It is the responsibility of the user to comply with all applicable laws and regulations and to provide for a safe workplace. The user should consider any health or safety hazards or information contained herein only as a guide, and should take those precautions which are necessary or prudent to instruct employees and to develop work practice procedures in order to promote a safe work environment. Further, nothing contained herein shall be taken as an inducement or recommendation to manufacture or use any of the herein materials or processes in violation of existing or future patent.

Technical data sheets may change frequently. You can download the latest version from our website www.albemarle-lithium.com. Please contact us at www.albemarle-lithium.com/contact with questions.

Product Number: 408586
Date of Issue: 2017/09/06

Crystallization temperature	< -10 °C
Flash point	-10 °C (2-Methyltetrahydrofuran)
Boiling point/boiling range	78 °C (2-Methyltetrahydrofuran)
Density	ca. 1.08 g/cm ³ at 20 °C
Water solubility	(Not applicable)
Molecular weight	147.30 g/mol
Thermal Stability	Crystallization below around -10 °C

HANDLING & STORAGE

Handling	Organomagnesium compounds must be handled under inert gas (nitrogen or argon). Never add water, acids oxidizing materials to the product. In case of fire use water or CO ₂ -extinguishers. Pay attention official safety regulations (see also 'Transport regulations' and GHS Hazard Pictograms).
Storage	Under exclusion of air and humidity stable over practically unlimited periods. Keep container dry and tightly closed. Material starts to crystallize below -10 °C.

TRANSPORT & PACKAGING

UN number 3399

ADR	Class: 4.3	PG: I	Label: 4.3 (3)
RID	Class: 4.3	PG: I	Label: 4.3 (3)
IMDG	Class: 4.3	PG: I	Label: 4.3 (3)
IATA_C	Class: 4.3	PG: I	Packing instruction (cargo aircraft): 494
IATA_P	Class: 4.3	PG: I	

The information presented herein is believed to be accurate and reliable, but is presented without guarantee or responsibility on the part of Albemarle Corporation and its subsidiaries and affiliates. It is the responsibility of the user to comply with all applicable laws and regulations and to provide for a safe workplace. The user should consider any health or safety hazards or information contained herein only as a guide, and should take those precautions which are necessary or prudent to instruct employees and to develop work practice procedures in order to promote a safe work environment. Further, nothing contained herein shall be taken as an inducement or recommendation to manufacture or use any of the herein materials or processes in violation of existing or future patent.

Technical data sheets may change frequently. You can download the latest version from our website www.albemarle-lithium.com. Please contact us at www.albemarle-lithium.com/contact with questions.

Product Number: 408586
Date of Issue: 2017/09/06

Hazard pictograms



Signal Word	Danger
H&P Phrases	See Safety Data Sheet
Labelling	The labelling is according to EU-GHS classification ((EG) 1272/2008) and may vary in other countries. Please refer to the respective Safety Data Sheet for your country.

Packaging

Glass bottles of 100, 250, 500 and 1,000 ml. Steel bottles with volumes of 7.4, 27, 127 or 450 l. For safety reasons these are filled to a maximum of 90 %. Steel drums up to 200 l.

OTHER INFORMATION

Further Related Documents	Safety Data Sheet
Our brochure(s)	Organomagnesium Compounds, Turbo Grignards - Li powered metalation, Turbo Grignards - Lithium powered Halogen/Magnesium Exchange, Organometallic Reactions in Green Solvents

The information presented herein is believed to be accurate and reliable, but is presented without guarantee or responsibility on the part of Albemarle Corporation and its subsidiaries and affiliates. It is the responsibility of the user to comply with all applicable laws and regulations and to provide for a safe workplace. The user should consider any health or safety hazards or information contained herein only as a guide, and should take those precautions which are necessary or prudent to instruct employees and to develop work practice procedures in order to promote a safe work environment. Further, nothing contained herein shall be taken as an inducement or recommendation to manufacture or use any of the herein materials or processes in violation of existing or future patent.

Technical data sheets may change frequently. You can download the latest version from our website www.albemarle-lithium.com. Please contact us at www.albemarle-lithium.com/contact with questions.