

TECHNICAL DATA SHEET

Date of Issue: 2016/08/24

Cesium Fluoride, purity min. 99.99 %

CAS-No. 13400-13-0

EC-No. 236-487-3

Molecular Formula CsF

Product Number 424021

APPLICATION

Cesium fluoride is a fluorination agent for halide exchange reactions. It is a versatile base in organic synthesis and can be used in e.g. in polymerization reactions, in brazing fluxes and in crystal growth applications.

PURITY

min. 99.99 %

SPECIFICATION

Li	max. 1 ppm
Na	max. 10 ppm
K	max. 10 ppm
Rb	max. 10 ppm
Ca	max. 1 ppm
Mg	max. 1 ppm
Sr	max. 2 ppm
Ba	max. 5 ppm
Al	max. 2 ppm
Fe	max. 10 ppm
Cr	max. 3 ppm
Mn	max. 1 ppm
P2O5	max. 1 ppm
SO4	max. 50 ppm

The information presented herein is believed to be accurate and reliable, but is presented without guarantee or responsibility on the part of Albemarle Corporation and its subsidiaries and affiliates. It is the responsibility of the user to comply with all applicable laws and regulations and to provide for a safe workplace. The user should consider any health or safety hazards or information contained herein only as a guide, and should take those precautions which are necessary or prudent to instruct employees and to develop work practice procedures in order to promote a safe work environment. Further, nothing contained herein shall be taken as an inducement or recommendation to manufacture or use any of the herein materials or processes in violation of existing or future patent.

Technical data sheets may change frequently. You can download the latest version from our website www.albemarle-lithium.com. Please contact us at www.albemarle-lithium.com/contact with questions.

CO3	max. 100 ppm
Cl	max. 50 ppm
H2O (Karl Fischer)	max. 0.03 %
free acid as HF	max. 0.1 %

Deliveries are accompanied by a lot specific certificate of analysis. If any of these values is critical to your application, please let us know.

PHYSICAL PROPERTIES

Appearance	crystalline powder
Color	white
Melting point/ range	703 °C at 1,013 hPa Method: OECD Test Guideline 102
Boiling point/boiling range	1,251 °C
Density	ca. 4.64 g/cm ³ at 20 °C
Bulk density	2,000 - 3,200 kg/m ³
Water solubility	5,730 g/L at 25 °C
Molecular weight	151.90 g/mol

HANDLING & STORAGE

Handling	Handling in moist air should be avoided. Safe handling requires the safety precautions typical for inorganic fluorides. Thus, eyes or skin should not be exposed to cesium fluoride, otherwise severe irritation may result. Ingestion must be avoided because of the toxicity of fluoride.
Storage	Because of its hygroscopicity cesium fluoride should be stored in tightly closed containers.

The information presented herein is believed to be accurate and reliable, but is presented without guarantee or responsibility on the part of Albemarle Corporation and its subsidiaries and affiliates. It is the responsibility of the user to comply with all applicable laws and regulations and to provide for a safe workplace. The user should consider any health or safety hazards or information contained herein only as a guide, and should take those precautions which are necessary or prudent to instruct employees and to develop work practice procedures in order to promote a safe work environment. Further, nothing contained herein shall be taken as an inducement or recommendation to manufacture or use any of the herein materials or processes in violation of existing or future patent.

Technical data sheets may change frequently. You can download the latest version from our website www.albemarle-lithium.com. Please contact us at www.albemarle-lithium.com/contact with questions.

TRANSPORT & PACKAGING

UN number 3288

ADR	Class: 6.1	PG: II	Label: 6.1
RID	Class: 6.1	PG: II	Label: 6.1
IMDG	Class: 6.1	PG: II	Label: 6.1
IATA_C	Class: 6.1	PG: II	Packing instruction (cargo aircraft): 676
IATA_P	Class: 6.1	PG: II	Packing instruction (passenger aircraft): 669

Hazard pictograms



Signal Word Danger

H&P Phrases See Safety Data Sheet

Labelling The labelling is according to EU-GHS classification ((EG) 1272/2008) and may vary in other countries. Please refer to the respective Safety Data Sheet for your country.

Packaging

Glass bottles or PE bags with aluminium barrier in drums (fiber drums, clamping ring drums, steel drums, steel drums with polypropylene inner lining). The aluminium barrier prevents diffusion of moisture into the product.

Alternative packaging on request. Smaller units are available at surcharge.

OTHER INFORMATION

Further Related Safety Data Sheet
Documents

The information presented herein is believed to be accurate and reliable, but is presented without guarantee or responsibility on the part of Albemarle Corporation and its subsidiaries and affiliates. It is the responsibility of the user to comply with all applicable laws and regulations and to provide for a safe workplace. The user should consider any health or safety hazards or information contained herein only as a guide, and should take those precautions which are necessary or prudent to instruct employees and to develop work practice procedures in order to promote a safe work environment. Further, nothing contained herein shall be taken as an inducement or recommendation to manufacture or use any of the herein materials or processes in violation of existing or future patent.

Technical data sheets may change frequently. You can download the latest version from our website www.albemarle-lithium.com. Please contact us at www.albemarle-lithium.com/contact with questions.