

# TECHNICAL DATA SHEET

Date of Issue: 2016/09/02

## Zirconium Nickel alloy 70/30 B

Molecular Formula      ZrNi

Product Number        453440

---

### APPLICATION

Zirconium/Nickel alloy powders find application in various pyrotechnic and ordnance areas. They are used in squibs, delay mixtures and initiators.

---

### FURTHER INGREDIENTS

Nickel powder

CAS-No.                7440-02-0

EC-No.                 231-111-4

Zirconium powder (non pyrophoric)

CAS-No.                7440-67-7

EC-No.                 231-176-9

Hafnium

CAS-No.                7440-58-6

EC-No.                 231-166-4

---

### SPECIFICATION

---

Auto Ignition Temperature	> 225 °C
Combustion Rate	1,400 +/- 600 sec/50 cm
Particle Size	min. 99.9 % < 45 µm
Average Particle Size	4 +/- 2 µm
Zr + Hf content	70 +/- 3 %
Ni content	30 +/- 3 %
(Zr + Hf) + Ni content	> 97 %
Fe	max. 0.20 %
Ca	max. 0.15 %
Al	max. 0.15 %
S	max. 0.01 %
H	max. 1.5 %

---

The information presented herein is believed to be accurate and reliable, but is presented without guarantee or responsibility on the part of Albemarle Corporation and its subsidiaries and affiliates. It is the responsibility of the user to comply with all applicable laws and regulations and to provide for a safe workplace. The user should consider any health or safety hazards or information contained herein only as a guide, and should take those precautions which are necessary or prudent to instruct employees and to develop work practice procedures in order to promote a safe work environment. Further, nothing contained herein shall be taken as an inducement or recommendation to manufacture or use any of the herein materials or processes in violation of existing or future patent.

Technical data sheets may change frequently. You can download the latest version from our website [www.albemarle-lithium.com](http://www.albemarle-lithium.com). Please contact us at [www.albemarle-lithium.com/contact](http://www.albemarle-lithium.com/contact) with questions.

---

Moisture	max. 0.2 %
----------	------------

---

## METHOD OF ANALYSIS

Gravimetric determination of zirconium and nickel. Spectral analysis of accompanying impurities.  
Measurement of average particle size and combustion properties.

---

## PHYSICAL PROPERTIES

Appearance	powder
Color	gray black
Melting point/ range	1,140 - 1,650 °C
Bulk density	2,000 - 3,000 kg/m <sup>3</sup>
Water solubility	(practically insoluble)

---

## HANDLING & STORAGE

Handling	Highly flammable solid. Dust explosion hazard. Powders of these alloys are highly flammable and burn with intense heat. By appropriate mixing of types A and B which are comparable in their composition but quite different in regard to their combustion properties it is possible to adjust defined combustion rates. Mixtures are available upon request. Keep away from flames, sparks and heat sources. Use ground connected metallic apparatus to avoid sudden ignition by electrostatic discharge. In case of fire cover with dry sand or dry chemical/dolomite (powdered limestone). Never extinguish with water, carbon dioxide, or halocarbon. See our material safety data sheet and special precautionary advice for more information on safety.
Storage	Store in tightly closed containers. ZrNi grade 70/30 B can only be stored for a limited period of time. The product should be consumed within 3 months after the date stated at the respective CofA.

---

The information presented herein is believed to be accurate and reliable, but is presented without guarantee or responsibility on the part of Albemarle Corporation and its subsidiaries and affiliates. It is the responsibility of the user to comply with all applicable laws and regulations and to provide for a safe workplace. The user should consider any health or safety hazards or information contained herein only as a guide, and should take those precautions which are necessary or prudent to instruct employees and to develop work practice procedures in order to promote a safe work environment. Further, nothing contained herein shall be taken as an inducement or recommendation to manufacture or use any of the herein materials or processes in violation of existing or future patent.

Technical data sheets may change frequently. You can download the latest version from our website [www.albemarle-lithium.com](http://www.albemarle-lithium.com). Please contact us at [www.albemarle-lithium.com/contact](http://www.albemarle-lithium.com/contact) with questions.

## TRANSPORT & PACKAGING

UN number 3089

ADR	Class: 4.1	PG: II	Label: 4.1
RID	Class: 4.1	PG: II	Label: 4.1
IMDG	Class: 4.1	PG: II	Label: 4.1
IATA_C	Class: 4.1	PG: II	Packing instruction (cargo aircraft): 448
IATA_P	Class: 4.1	PG: II	Packing instruction (passenger aircraft): 445

Hazard pictograms



Signal Word                      Danger

H&P Phrases                      See Safety Data Sheet

Labelling                              The labelling is according to EU-GHS classification ((EG) 1272/2008) and may vary in other countries. Please refer to the respective Safety Data Sheet for your country.

Packaging

Passenger aircraft: tin cans of 2.5 kg. Cargo aircraft only: tin cans of 5 kg. Other packaging sizes on request.

## OTHER INFORMATION

Further Related                      Safety Data Sheet  
Documents

The information presented herein is believed to be accurate and reliable, but is presented without guarantee or responsibility on the part of Albemarle Corporation and its subsidiaries and affiliates. It is the responsibility of the user to comply with all applicable laws and regulations and to provide for a safe workplace. The user should consider any health or safety hazards or information contained herein only as a guide, and should take those precautions which are necessary or prudent to instruct employees and to develop work practice procedures in order to promote a safe work environment. Further, nothing contained herein shall be taken as an inducement or recommendation to manufacture or use any of the herein materials or processes in violation of existing or future patent.

Technical data sheets may change frequently. You can download the latest version from our website [www.albemarle-lithium.com](http://www.albemarle-lithium.com). Please contact us at [www.albemarle-lithium.com/contact](http://www.albemarle-lithium.com/contact) with questions.