

# ETHACURE<sup>®</sup> 420 Curative

## DESCRIPTION

ETHACURE 420 curative is an effective curing agent for polyurethanes. It can be used as a chain extender for polyurethane and polyurea elastomers, rigid and flexible foams, adhesives and joint sealants as well as in spray applications.

## TYPICAL PROPERTIES

Appearance	clear, yellow liquid *
Molecular weight g/mol	310.48
Boiling point °F (°C)	825.8 (441)
Density at 68°F (20°C), g/ml	0.991
Density at 68°F (20°C), lb/gal	8.50
Viscosity at 68°F (20°C), cP	570.2
Viscosity at 77°F (25°C), cP	336.9
Equivalent weight with isocyanates	155

An asterisk (\*) indicates that this will darken upon exposure to air. Store product at the temperature above ambient temperature.

## SHIPPING INFORMATION

### Container sizes:

Tank cars  
Tank trailers  
Drums: 5- and 55-gal, nonreturnable steel

### Shipping classification:

DOT description/proper shipping name:  
Not regulated for transportation

### Other information:

US TSCA Chemical Inventory Number: CAS 5285-60-9  
EINECS: Listed  
MITI: Listed

## SAFETY AND HANDLING INFORMATION

Before handling or using this product, the material safety data sheet should be read and understood. This can be obtained from your Albemarle sales representative.



NORTH AMERICA 4350 Congress Street, Suite 700 • Charlotte, North Carolina 28209 • Tel: +1 980 299 5700  
EUROPE Industriepark Höchst, Gebäude G 879, 5926 Frankfurt am Main, Germany • Tel: +49 69 40 12 60  
LATIN AMERICA Isidora Goyenechea Nro. 3162, Oficina 202, Las Condes • Santiago, Chile • Tel: +56-55-2351008  
ASIA PACIFIC Albemarle Management (Shanghai) Co. Ltd. • Building 6, A-Sun Science & Technology Park, Lane 399 Shengxia Road  
Pudong, Shanghai 201210, China • Tel: +86-21-6103-8666

The information presented herein is believed to be accurate and reliable, but is presented without guarantee or responsibility on the part of Albemarle Corporation and its subsidiaries to ensure the accuracy or reliability of the information. It is the responsibility of the user to comply with all applicable laws and regulations and to provide for a safe workplace. The user should consider all information contained herein only as a guide, and should take precautions that the user considers necessary or prudent to promote a safe work environment, such as considering all applicable health and safety hazards, developing safe work practice procedures and properly instructing employees. Further, nothing contained herein shall be taken as an inducement or recommendation to manufacture or use any of the materials or processes mentioned herein in violation of existing or pending patents.