

# ETHACURE<sup>®</sup> 270 Curative

## DESCRIPTION

ETHACURE 270 curative is an effective curing agent for curing liquid epoxy resins at ambient and elevated temperatures. ETHACURE 270 exhibits longer pot life than conventional cycloaliphatic amines and after cured can deliver excellent mechanical strength, high temperature performance and chemical resistance.

## TYPICAL PROPERTIES

Appearance	clear, yellow liquid *
Flash point, °F (°C)	282 (139) (closed cup)
Boiling point °F (°C)	549 (287)
Density at 20°C g/ml	0.99
Solubility	
Water	Partially miscible
Toluene	Miscible
Methanol	Miscible
Heptane	Partially miscible
Viscosity at 20°C	158 cSt
Viscosity at 25°C	87 cSt
Viscosity at 40°C	31 cSt
Molecule weight	175.7
Active hydrogen equiv. wt	43.9

*An asterisk (\*) indicates that this will darken upon exposure to air.*



NORTH AMERICA 4350 Congress Street, Suite 700 • Charlotte, North Carolina 28209 • Tel: +1 980 299 5700  
EUROPE Industriepark Höchst, Gebäude G 879, 5926 Frankfurt am Main, Germany • Tel: +49 69 40 12 60  
LATIN AMERICA Isidora Goyenechea Nro. 3162, Oficina 202, Las Condes • Santiago, Chile • Tel: +56-55-2351008  
ASIA PACIFIC Albemarle Management (Shanghai) Co. Ltd. • Building 6, A-Sun Science & Technology Park, Lane 399 Shengxia Road  
Pudong, Shanghai 201210, China • Tel: +86-21-6103-8666

The information presented herein is believed to be accurate and reliable, but is presented without guarantee or responsibility on the part of Albemarle Corporation and its subsidiaries to ensure the accuracy or reliability of the information. It is the responsibility of the user to comply with all applicable laws and regulations and to provide for a safe workplace. The user should consider all information contained herein only as a guide, and should take precautions that the user considers necessary or prudent to promote a safe work environment, such as considering all applicable health and safety hazards, developing safe work practice procedures and properly instructing employees. Further, nothing contained herein shall be taken as an inducement or recommendation to manufacture or use any of the materials or processes mentioned herein in violation of existing or pending patents.